

BITUMEN

60-70



PROPERTIES	RESULT	TEST METHOD
Specific gravity@25/25°C	1.01 - 16	ASTM D70
Penetration@25°C, 5	60 - 70	ASTM D5
Softening point °C	49.56	ASTM D36
Ductility@25°C	100 min	ASTM D113
Loss on heating (wt%)	0.2 max	ASTM D6
Drop-in penetration	20 max	ASTM D6 & D5
Flash point	250 min	ASTM D92
Solubility in C2 (wt%)	99.5 min	ASTM D4
Spot test	Negative	A.A.S.H.O.T 102

TAJIK OIL REFINING

The analysis will be customizable & produce able as per buyer's request